



C041 - 2K Ultra Pro Clear

NORTH AMERICAN MARKET

Product Description

The C041 2K Ultra Pro Clear is a top of the line high solid, high build clearcoat with excellent vertical stability and distinctness image.

Suitable Substrates

- Hyflow basecoat
- Hydrobase basecoat

Product Application



Mix 2:1 with any of the following Hymax hardeners:


- H036 2K Hardener Slow
- H023 2K Hardener Normal
- H015 2K Hardener Fast

Potlife: 4h at 20°C (68°F)




20-22s / # 2 Zahn @ 68°F

Potlife: 4h at 20°C



HVLP 1.3 – 1.5 mm (2 spray passes)
2.5 bar inlet pressure (36 PSI)



0.8-1.0 Mil per full coat

Disclaimer: Users assume full responsibility for any consequences resulting from the incorrect usage of our products.

NORTH AMERICAN MARKET



Wait 12-14 min before increasing temperature
Bake 20 min at 60°C (140°F) panel temperature



Short Wave 8 min
The object should be maintained at greater than 80 cm from source.



Wear suitable protection

Product Characteristics

VOC: Regulatory VOC 505.2 gr/lit (4.2 lbs/gal) Regulatory VOC ready to spray < 498.5 gr/lit (4.15 lbs/gal)

Specific Gravity: 0.966 kg/lit (8.04 lbs/gal)

Solid Content: 46.0 – 47.0 % by weight RFU

Coverage: 700 ft²/gal at 1 dry mil dry film thickness (theoretical)

SDS: Refer to the Safety Data Sheet

Disclaimer: Users assume full responsibility for any consequences resulting from the incorrect usage of our products.